



Mirel P1002

Injection Molding Grade

Environmental Innovation

Environmental responsibility is a major trend among industry leading brand owners and OEMs. Mirel is a new family of biobased resin providing the industry with sustainable alternatives to conventional plastics. Mirel meets the demands of environmentally-conscious companies and consumers making a positive impact on global climate change. Mirel starts with nature and ends with nature. It harmlessly biodegrades in all of these environments:

- Industrial and home composting
- Soil
- Municipal waste treatment facilities, septic systems
- Wetlands, streams, and oceans

Mirel™ P1002 is a high performance, semi-crystalline natural polyester specifically engineered for injection molding applications. Mirel resins are innovative and versatile solutions suitable for a wide variety of product applications.

Product Attributes

- Higher flow
- Heat resistance
- Medium stiffness
- Easy Processing

Biodegradation Certifications and Testing

Mirel resins are certified to ASTM D6400 / EN 13432 for compostable plastics, and D7081 / EN 17556 for non-floating biodegradable plastics in marine environment.

Test results from ASTM D5988-96 / ISO 17556 for aerobic biodegradation in soil of plastics or residual plastics materials show that Mirel fully biodegrades - fungal/bacterial under ambient conditions.

Test results from ASTM D5209 / ISO 14852 / ASTM D5271 / ISO 14851 for aerobic biodegradation of plastic materials in an activated-sludge wastewater-treatment system show that Mirel fully biodegrades - bacterial under ambient conditions.

Potential Applications

Food service ware

- Single serve containers, caps, lids and trays

Consumer and packaging

- Cosmetic cases and lipsticks

Physical Properties	ASTM Typical Value	ASTM Test Method	ISO Typical Value	ISO Test Method
Mold Shrinkage	0.014 - 0.016 in/in	ASTM D955		
Water Absorption @ 24 hrs (73° F)	0.10%	ASTM D570		
Apparent Melt Viscosity (180° C, 100 sec-1)	1000 Pa-s	ASTM 3835		
Specific Gravity	1.30 g/cm ³	ASTM D792		
Mechanical Properties				
Tensile strength @ yield	3900 psi	ASTM D638	26 MPa	ISO 527-1, -2
Tensile elongation @ break	15%	ASTM D638	13%	ISO 527-1, -2
Flexural modulus	260,000 psi	ASTM D790 A	1900 MPa	ISO 178
Flexural strength	6000 psi	ASTM D790 A	35 MPa	ISO 178
Impact				
Notched Izod	0.6 ft-lbs/in	ASTM D256 A	3.2 kJ/m ²	ISO 180 A
Thermal				
DTUL @66 psi / 0.45 MPa	259° F	ASTM D648 B	116° C	ISO 75-1 B
DTUL @264 psi / 1.80 MPa	151° F	ASTM D648 B	61° C	ISO 75-1 A
Vicat Softening Point	279° F	ASTM D1525 A10	137° C	ISO 306 A50

All physical properties are measured after 21 day aging.



Injection Molding Processing Information

Start-up

Before processing Mirel, the injection unit and all melt train components should first be purged with high-flow LDPE compound. Starting with a barrel temperature of 170° C, the material should be kept moving during start-up and purged until there are no visual contaminants in the purge material. This suggests a minimum of 20 purge shots be taken prior to sampling. All adjustments to the mold or other auxiliary equipment should be completed prior to start up.

Shut down


After processing Mirel, the injection unit and all melt train components should be purged with high-flow LDPE.

Safety information

Please refer to the MSDS sheet for safety, health and proper disposal recommendations.

Material Recommendations	
Drying Conditions (Dessicant)	2 to 4 hours @ 80° C
Melt Temperature	160° C to 165° C
Equipment Recommendations	
Screw Profile (Low Shear GP)	2.2:1 to 2.6:1
Non-Return Valve	Std Check Ring
Processing Conditions	
Barrel Zone Settings	Reverse Temperature Profile
Rear	175° C to 180° C
Middle	170° C to 175° C
Front	165° C to 170° C
Nozzle	165° C to 170° C
Mold Temperature (A/B)	55° C to 65° C
Screw Speed (Slow)	< 200 RPM
Back Pressure (Low)	< 500 PSI (Melt)
2nd Stage Pressure (Low)	< 30% of 1st Stage Pressure

Viscosity versus Shear Rate



- Mirel P1002, 180° C
- Profax 6323 (PP), 200° C
- Cicolac GPM 5500 (ABS), 230° C

For further information please contact: 1.866.916.4735 (1.866.91MIREL)

By combining bioscience and nature we bring a clean solution to the world with Mirel.

www.telles-mirel.com

NOTICE: The information contained herein is believed to be reliable, but no representations, guarantees or warranties of any kind are made as to its accuracy or the suitability of the material for particular applications. This information is based on laboratory work with small-scale equipment and does not necessarily indicate end product performance. The customer assumes all risk and liability of any use or handling of any material beyond Telles direct control. Telles and Metabolix make NO WARRANTIES, EXPRESS OR IMPLIED, INCLUDING, BUT NOT LIMITED TO, THE IMPLIED WARRANTIES OF MERCHANTABILITY AND FITNESS FOR A PARTICULAR PURPOSE.